

---

---

**Welding consumables — Solid wires  
and rods for fusion welding of copper  
and copper alloys — Classification**

*Produits consommables pour le soudage — Fils pleins et baguettes  
pleines pour le soudage par fusion du cuivre et des alliages de cuivre —  
Classification*

STANDARDSISO.COM : Click to view the full PDF of ISO 24373:2008



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 24373:2008



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 24373 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

Requests for official interpretations of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 3 via your national standards body, a complete listing of which can be found at [www.iso.org](http://www.iso.org).

## Introduction

For copper-welding consumables, there is no unique relationship between the product form (solid wire or rod) and the welding process used (e.g. gas-shielded metal arc welding, gas tungsten arc welding, plasma arc or other welding processes). For this reason, the solid wires or rods may be classified on the basis of any of the above product forms and can be used, as appropriate, for more than one of the above processes.

ISO 24373 is based on EN 14640:2005.

STANDARDSISO.COM : Click to view the full PDF of ISO 24373:2008

# Welding consumables — Solid wires and rods for fusion welding of copper and copper alloys — Classification

## 1 Scope

This International Standard specifies requirements for classification of solid wires and rods for fusion welding of copper and copper alloys. The classification of the solid wires and rods is based on their chemical composition.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 31-0:1992, *Quantities and units — Part 0: General principles*

ISO 544, *Welding consumables — Technical delivery conditions for welding filler materials — Type of product, dimensions, tolerances and markings*

ISO 4063, *Welding and allied processes — Nomenclature of processes and reference numbers*

ISO 14344, *Welding and allied processes — Flux and gas shielded electrical welding processes — Procurement guidelines for consumables*

## 3 Classification

The classification is divided into two parts:

- a) the first part indicates the product form, solid wires or rods (see 4.1);
- b) the second part gives a numerical symbol indicating the chemical composition of the solid wire or rod (see Table 1).

## 4 Symbols

### 4.1 Symbol for the product form

The symbol for the solid wire and rod shall be S.

NOTE One product form may be used for more than one welding process.

## 4.2 Symbol for the chemical composition

The numerical symbol in Table 1 indicates the chemical composition of a solid wire or rod, determined under conditions given in Clause 6.

NOTE 1 In addition the chemical symbol may be used.

NOTE 2 Corresponding national classifications are shown in Annex A.

## 5 Mechanical properties of the weld metal

The mechanical properties of the weld metal are not part of the classification.

## 6 Chemical analysis

Chemical analysis shall be performed on specimens of the product or the stock from which it is made. Any analytical technique can be used; but, in case of dispute, reference shall be made to established published methods, agreed between the contracting parties.

## 7 Rounding-off procedure

For purposes of determining compliance with the requirements of this International Standard, the actual test values obtained shall be subjected to the rounding-off rules of ISO 31-0:1992, Annex B, Rule A. If the measured values are obtained by equipment calibrated in units other than those of this International Standard, the measured values shall be converted to the units of this International Standard before rounding off. If an average value is to be compared to the requirements of this International Standard, rounding off shall be done only after calculating the average. In the case where the testing standard cited in the normative references of this International Standard contains instructions for rounding off that conflict with the instructions of this International Standard, the rounding off requirements of the testing standard shall apply. The rounded-off results shall fulfil the requirements of the appropriate table for the classification under test.

## 8 Retest

If any test fails to meet a requirement, that test shall be repeated twice. The results of both retests shall meet the requirement. Specimens for the retest may be taken from the original test sample or from a new test sample. For chemical analysis, retests need only be for those specific elements that failed to meet their test requirement. If the results of one or both retests fail to meet the requirement, the material under test shall be considered as not meeting the requirements of this International Standard for that classification.

In the event that, during preparation or after completion of any test, it is clearly determined that prescribed or proper procedures were not followed in preparing the sample or test specimen(s), or in conducting the tests, the test shall be considered invalid, without regard to whether the test was actually completed, or whether the test results met, or failed to meet, the requirement. That test shall be repeated, following proper prescribed procedures. In this case, the requirement for doubling the number of test specimens does not apply.

## 9 Technical delivery conditions

Technical delivery conditions shall meet the requirements in ISO 544 and ISO 14344.

Table 1 — Symbol for the chemical composition of solid wires and rods

| Alloy symbols                      |                | Chemical composition, % mass fraction <sup>a, b</sup> |       |              |              |             |              |       |              |              |      |      |   |    |   |                  |
|------------------------------------|----------------|-------------------------------------------------------|-------|--------------|--------------|-------------|--------------|-------|--------------|--------------|------|------|---|----|---|------------------|
| Numerical                          | Chemical       | Cu                                                    | Al    | Fe           | Mn           | Ni incl. Co | P            | Pb    | Si           | Sn           | Zn   | As   | C | Ti | S | Others total     |
| COPPER-LOW ALLOYED                 |                |                                                       |       |              |              |             |              |       |              |              |      |      |   |    |   |                  |
| Cu 1897                            | CuAg1          | min. 99,5 incl. Ag                                    | 0,01  | 0,05         | 0,2          | 0,3         | 0,01 to 0,05 | 0,01  | 0,1          | —            | —    | 0,05 | — | —  | — | 0,2 Ag0,8 to 1,2 |
| Cu 1898                            | CuSn1          | min. 98,0                                             | 0,01  | —            | 0,50         | —           | 0,15         | 0,02  | 0,5          | 1,0          | —    | —    | — | —  | — | 0,50             |
| Cu 1898A                           | CuSn1MnSi      | bal.                                                  | 0,01  | 0,03         | 0,1 to 0,4   | 0,1         | 0,015        | 0,01  | 0,1 to 0,4   | 0,5 to 1,0   | —    | —    | — | —  | — | 0,2              |
| COPPER-SILICON (SILICON BRONZE)    |                |                                                       |       |              |              |             |              |       |              |              |      |      |   |    |   |                  |
| Cu 6511                            | CuSi2Mn1       | bal.                                                  | 0,01  | 0,1          | 0,5 to 1,5   | —           | 0,02         | 0,02  | 1,5 to 2,0   | 0,1 to 0,3   | 0,2  | —    | — | —  | — | 0,5              |
| Cu 6560                            | CuSi3Mn1       | bal.                                                  | 0,02  | 0,5          | 0,5 to 1,5   | —           | 0,05         | 0,02  | 2,8 to 4,0   | 0,2          | 0,4  | —    | — | —  | — | 0,5              |
| Cu 6561                            | CuSi2Mn1Sn1Zn1 | bal.                                                  | —     | 0,5          | 1,5          | —           | —            | 0,02  | 2,0 to 2,8   | 1,5          | 1,5  | —    | — | —  | — | 0,5              |
| COPPER-TIN (INCL. PHOSPHOR BRONZE) |                |                                                       |       |              |              |             |              |       |              |              |      |      |   |    |   |                  |
| Cu 5180                            | CuSn5P         | bal.                                                  | 0,01  | —            | —            | —           | 0,1 to 0,4   | 0,02  | —            | 4,0 to 6,0   | —    | —    | — | —  | — | 0,5              |
| Cu 5180A                           | CuSn6P         | bal.                                                  | 0,01  | 0,1          | —            | —           | 0,01 to 0,4  | 0,02  | —            | 4,0 to 7,0   | 0,1  | —    | — | —  | — | 0,2              |
| Cu 5210                            | CuSn8P         | bal.                                                  | —     | 0,1          | —            | 0,2         | 0,01 to 0,4  | 0,02  | —            | 7,5 to 8,5   | 0,2  | —    | — | —  | — | 0,2              |
| Cu 5211                            | CuSn10MnSi     | bal.                                                  | 0,01  | 0,1          | 0,1 to 0,5   | —           | 0,1          | 0,02  | 0,1 to 0,5   | 9,0 to 10,0  | 0,1  | —    | — | —  | — | 0,5              |
| Cu 5410                            | CuSn12P        | bal.                                                  | 0,005 | —            | —            | —           | 0,01 to 0,4  | 0,02  | —            | 11,0 to 13,0 | 0,05 | —    | — | —  | — | 0,4              |
| COPPER-ZINC (BRASS)                |                |                                                       |       |              |              |             |              |       |              |              |      |      |   |    |   |                  |
| Cu 4641                            | CuZn40SnSi     | 58,0 to 62,0                                          | 0,01  | 0,2          | 0,3          | —           | —            | 0,03  | 0,1 to 0,5   | 1,0          | bal. | —    | — | —  | — | 0,2              |
| Cu 4700                            | CuZn40Sn       | 57,0 to 61,0                                          | 0,01* | *            | *            | —           | —            | 0,05* | *            | 0,25 to 1,00 | bal. | —    | — | —  | — | 0,5 <sup>c</sup> |
| Cu 4701                            | CuZn40SnSiMn   | 58,5 to 61,5                                          | 0,01  | 0,25         | 0,05 to 0,25 | —           | —            | 0,02  | 0,15 to 0,4  | 0,2 to 0,5   | bal. | —    | — | —  | — | 0,2              |
| Cu 6800                            | CuZn40Ni       | 56,0 to 60,0                                          | 0,01* | 0,25 to 1,20 | 0,01 to 0,50 | 0,2 to 0,8  | —            | 0,05* | 0,04 to 0,20 | 0,8 to 1,1   | bal. | —    | — | —  | — | 0,5 <sup>c</sup> |

Table 1 (continued)

| Alloy symbols                       |                 | Chemical composition, % mass fraction <sup>a, b</sup> |              |              |              |              |      |       |              |            |      |    |      |            |      |                  |
|-------------------------------------|-----------------|-------------------------------------------------------|--------------|--------------|--------------|--------------|------|-------|--------------|------------|------|----|------|------------|------|------------------|
| Numerical                           | Chemical        | Cu                                                    | Al           | Fe           | Mn           | Ni incl. Co  | P    | Pb    | Si           | Sn         | Zn   | As | C    | Ti         | S    | Others total     |
| Cu 6810                             | CuZn40Fe1Sn1    | 56,0 to 60,0                                          | 0,01*        | 0,25 to 1,20 | 0,01 to 0,50 | —            | —    | 0,05* | 0,04 to 0,15 | 0,8 to 1,1 | bal. | —  | —    | —          | —    | 0,5 <sup>c</sup> |
| Cu 7730                             | CuZn40Ni10      | 46,0 to 50,0                                          | 0,01*        | —            | —            | 9,0 to 11,0  | 0,25 | 0,05* | 0,04 to 0,25 | —          | bal. | —  | —    | —          | —    | 0,5 <sup>c</sup> |
| COPPER-ALUMINIUM (ALUMINIUM BRONZE) |                 |                                                       |              |              |              |              |      |       |              |            |      |    |      |            |      |                  |
| Cu 6061                             | CuAl5Ni2Mn      | bal.                                                  | 4,5 to 5,5   | 0,5          | 0,1 to 1,0   | 1,0 to 2,5   | —    | 0,02  | 0,1          | —          | 0,2  | —  | —    | —          | —    | 0,5              |
| Cu 6100                             | CuAl7           | bal.                                                  | 6,0 to 8,5   | *            | 0,5          | *            | —    | 0,02  | 0,2          | *          | 0,2  | —  | —    | —          | —    | 0,4 <sup>c</sup> |
| Cu 6180                             | CuAl10Fe        | bal.                                                  | 8,5 to 11,0  | 1,5          | —            | —            | —    | 0,02  | 0,1          | —          | 0,02 | —  | —    | —          | —    | 0,5              |
| Cu 6240                             | CuAl11Fe3       | bal.                                                  | 10,0 to 11,5 | 2,0 to 4,5   | —            | —            | —    | 0,02  | 0,1          | —          | 0,1  | —  | —    | —          | —    | 0,5              |
| Cu 6325                             | CuAl8Fe4Mn2Ni2  | bal.                                                  | 7,0 to 9,0   | 1,8 to 5,0   | 0,5 to 3,0   | 0,5 to 3,0   | —    | 0,02  | 0,1          | —          | 0,1  | —  | —    | —          | —    | 0,4              |
| Cu 6327                             | CuAl8Ni2Fe2Mn2  | bal.                                                  | 7,0 to 9,5   | 0,5 to 2,5   | 0,5 to 2,5   | 0,5 to 3,0   | —    | 0,02  | 0,2          | —          | 0,2  | —  | —    | —          | —    | 0,4              |
| Cu 6328                             | CuAl9Ni5Fe3Mn2  | bal.                                                  | 8,5 to 9,5   | 3,0 to 5,0   | 0,6 to 3,5   | 4,0 to 5,5   | —    | 0,02  | 0,1          | —          | 0,1  | —  | —    | —          | —    | 0,5              |
| COPPER-MANGANESE                    |                 |                                                       |              |              |              |              |      |       |              |            |      |    |      |            |      |                  |
| Cu 6338                             | CuMn13Al8Fe3Ni2 | bal.                                                  | 7,0 to 8,5   | 2,0 to 4,0   | 11,0 to 14,0 | 1,5 to 3,0   | —    | 0,02  | 0,1          | —          | 0,15 | —  | —    | —          | —    | 0,5              |
| COPPER-NICKEL                       |                 |                                                       |              |              |              |              |      |       |              |            |      |    |      |            |      |                  |
| Cu 7061                             | CuNi10          | bal.                                                  | —            | 0,5 to 2,0   | 0,5 to 1,5   | 9,0 to 11,0  | 0,02 | 0,02  | 0,2          | —          | —    | —  | 0,05 | 0,1 to 0,5 | 0,02 | 0,4              |
| Cu 7158                             | CuNi30Mn1FeTi   | bal.                                                  | —            | 0,4 to 0,7   | 0,5 to 1,5   | 29,0 to 32,0 | 0,02 | 0,02  | 0,25         | —          | —    | —  | 0,04 | 0,2 to 0,5 | 0,01 | 0,5              |

<sup>a</sup> Analysis shall be made for the elements for which specific values are shown in this table. If, however, the presence of other elements is indicated in the course of routine analysis, further analyses shall be carried out to determine that the total of these other elements does not exceed the given maximum level.

<sup>b</sup> Single values shown are maxima, unless otherwise noted.

<sup>c</sup> (and \*) The total of all other elements, including those for which the maximum value or an asterisk (\*) is shown, shall not exceed the value specified in "Others total".

NOTE Consumables not listed in the table can be symbolized by Cu Z. The chemical symbol established by the manufacturer may be added in brackets.

## 10 Designation

The designation of solid wires and rods shall follow the principle given in the example below.

EXAMPLE A solid wire (S) for fusion welding that has a chemical composition within the limits for the alloy symbol Cu 6560 (CuSi3Mn1) of Table 1 is designated:

**Solid wire ISO 24373 - S Cu 6560**

or

**Solid wire ISO 24373 - S Cu 6560 (CuSi3Mn1)**

where:

ISO 24373 is the number of this International Standard;

S is the product form (see 4.1);

Cu 6560 is the chemical composition of welding consumable (see Table 1);

CuSi3Mn1 is the optional chemical composition of welding consumable (see Table 1).

**Annex A**  
(informative)

**Corresponding national classifications**

STANDARDSISO.COM : Click to view the full PDF of ISO 24373:2008

Table A.1 — Corresponding national classifications

| Numerical symbol                   | Chemical symbol | USA                                        |        | Japan                            | Europe             |               | Germany         |
|------------------------------------|-----------------|--------------------------------------------|--------|----------------------------------|--------------------|---------------|-----------------|
|                                    |                 | AWS A5.7/A5.7M:2007<br>AWS A5.8/A5.8M:2004 | UNS    | JIS Z3341:1999<br>JIS Z3202:1999 | EN 13347:2002      | EN 14640:2005 | DIN 1733-1:1998 |
| COPPER-(LOW ALLOYED)               |                 |                                            |        |                                  |                    |               |                 |
| Cu 1897                            | CuAg1           | —                                          | —      | —                                | —                  | CuAg1         | 2.1211          |
| Cu 1898                            | CuSn1           | ERCu                                       | C18980 | YCu                              | —                  | —             | —               |
| Cu 1898A                           | CuSn1MnSi       | —                                          | —      | —                                | CuSn1MnSi          | CuSn1         | 2.1006          |
| COPPER-SILICON (silicon bronze)    |                 |                                            |        |                                  |                    |               |                 |
| Cu 6511                            | CuSi2Mn1        | —                                          | —      | —                                | —                  | CuSi2Mn1      | —               |
| Cu 6560                            | CuSi3Mn1        | ERCuSi-A                                   | C65600 | YCuSi B                          | CuSi3Mn1           | CuSi3Mn1      | 2.1461          |
| Cu 6561                            | CuSi2Mn1Sn1Zn1  | —                                          | —      | YCuSi A                          | —                  | CuSi2Mn1Sn    | —               |
| COPPER-TIN (incl. phosphor bronze) |                 |                                            |        |                                  |                    |               |                 |
| Cu 5180                            | CuSn5P          | ERCuSn-A                                   | C51800 | YCuSn A                          | CuSn5, CuSn6       | —             | 2.1022          |
| Cu 5180A                           | CuSn6P          | ERCuSn-A                                   | C51800 | —                                | CuSn5, CuSn6       | CuSn6P        | 2.1022          |
| Cu 5210                            | CuSn8P          | —                                          | —      | YCuSn B                          | CuSn8              | CuSn9P        | —               |
| Cu 5211                            | CuSn10MnSi      | —                                          | —      | —                                | —                  | CuSn10        | —               |
| Cu 5410                            | CuSn12P         | —                                          | —      | —                                | CuSn12             | CuSn12P       | 2.1056          |
| COPPER-ZINC (brass)                |                 |                                            |        |                                  |                    |               |                 |
| Cu 4641                            | CuZn40SnSi      | —                                          | —      | —                                | CuZn40FeSiSn       | CuZn40SnSi    | —               |
| Cu 4700                            | CuZn40Sn        | RBCuZn-A                                   | C47000 | GCuZnSn                          | CuZn40Sn1          | CuZn40        | —               |
| Cu 4701                            | CuZn40SnSiMn    | —                                          | —      | —                                | CuZn40MnSiSn       | CuZn40SnSiMn  | —               |
| Cu 6800                            | CuZn40Ni        | RBCuZn-B                                   | C68000 | —                                | CuZn39Fe1Sn1MnNiSi | CuZn40Ni      | —               |
| Cu 6810                            | CuZn40Fe1Sn1    | RBCuZn-C                                   | C68100 | —                                | CuZn40FeSiSn       | CuZn40SnSi    | 2.0366          |
| Cu 7730                            | CuZn40Ni10Sn1   | RBCuZn-D                                   | C77300 | GCuZnNi                          | —                  | CuZn40Ni10    | —               |

Table A.1 (continued)

| Numerical symbol                    | Chemical symbol | USA                                        |        | Japan      | Europe         |               | Germany |
|-------------------------------------|-----------------|--------------------------------------------|--------|------------|----------------|---------------|---------|
|                                     |                 | AWS A5.7/A5.7M:2007<br>AWS A5.8/A5.8M:2004 | UNS    |            | EN 13347:2002  | EN 14640:2005 |         |
| COPPER-ALUMINIUM (aluminium bronze) |                 |                                            |        |            |                |               |         |
| Cu 6061                             | CuAl5Ni2Mn      | —                                          | —      | —          | —              | CuAl5Mn1Ni1   | —       |
| Cu 6100                             | CuAl7           | ERCuAl-A1                                  | C61000 | —          | CuAl8          | CuAl8         | 2.0921  |
| Cu 6180                             | CuAl10Fe1       | ERCuAl-A2                                  | C61800 | YCulAl     | CuAl10Fe1      | CuAl10        | 2.0937  |
| Cu 6240                             | CuAl11Fe3       | ERCuAl-A3                                  | C62400 | —          | —              | CuAl11Fe      | —       |
| Cu 6325                             | CuAl8Fe4Mn2Ni2  | —                                          | —      | YCulAlNi B | —              | CuAl8Fe4Ni2   | —       |
| Cu 6327                             | CuAl8Ni2Fe2Mn2  | —                                          | —      | YCulAlNi A | —              | CuAl8Ni2      | 2.0922  |
| Cu 6328                             | CuAl9Ni5Fe3Mn2  | ERCuAlNi                                   | C63280 | YCulAlNi C | CuAl9Ni4Fe3Mn2 | CuAl9Ni5      | 2.0923  |
| COPPER-MANGANESE                    |                 |                                            |        |            |                |               |         |
| Cu 6338                             | CuMn13Al8Fe3Ni2 | ERCuMnNiAl                                 | C63380 | —          | —              | CuMn13Al7     | 2.1367  |
| COPPER-NICKEL                       |                 |                                            |        |            |                |               |         |
| Cu 7061                             | CuNi10          | —                                          | —      | YCulNi-1   | —              | CuNi10        | 2.0873  |
| Cu 7158                             | CuNi30Mn1FeTi   | ERCuNi                                     | C71581 | YCulNi-3   | —              | CuNi30        | 2.0837  |