



400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard



AMS 3228H

Issued DEC 1942
Revised SEP 1996

Superseding AMS 3228G

ACRYLONITRILE BUTADIENE (NBR) RUBBER
Hot Oil and Coolant Resistant, Low Swell
65-75

This specification has been "CANCELLED" by the Aerospace Materials Division, SAE, as of September 1996. By this action, the document revision letter and title will be deleted from the active specification index of Aerospace Material Specifications. Cancelled specifications are available from SAE upon request.

SAENORM.COM : Click to view the full PDF of ams3228h

PREPARED UNDER THE JURISDICTION OF AMS COMMITTEE "CE"

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1996 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 3228G

Issued 1 DEC 1942
Revised 1 JAN 1992

Superseding AMS 3228F

Submitted for recognition as an American National Standard

ACRYLONITRILE BUTADIENE (NBR) RUBBER
Hot Oil and Coolant Resistant, Low Swell
65 - 75

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of April 30, 1991. It is recommended, therefore, that this specification not be specified for new designs.

This cover sheet should be attached to the "F" revision of the subject specification.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE upon request.

PREPARED UNDER THE JURISDICTION OF AMS COMMITTEE "CE".

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

ACRYLONITRILE BUTADIENE (NBR) RUBBER
Hot Oil and Coolant Resistant, Low Swell
65 - 75

1. SCOPE:

1.1 Form: This specification covers a nitrile (NBR) rubber in the form of sheet, strip, tubing, extrusions, and molded shapes.

1.2 Application: Primarily for hose, packings, bushings, grommets, and seals in contact with hot, petroleum-base lubricating oils and glycol-type coolants from -40° to +100°C (-40° to +212°F).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 2810 - Identification and Packaging, Elastomeric Products

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D297 - Rubber Products - Chemical Analysis

ASTM D395 - Rubber Property - Compression Set

ASTM D412 - Rubber Properties in Tension

ASTM D471 - Rubber Property - Effect of Liquids

ASTM D573 - Rubber Deterioration in an Air Oven

ASTM D2137 - Rubber Property - Brittleness Point of Flexible Polymers and Coated Fabrics

ASTM D2240 - Rubber Property - Durometer Hardness

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

AMS 3228F

3. TECHNICAL REQUIREMENTS:

3.1 Material: Shall be a compound based on an acrylonitrile-butadiene (NBR) elastomer, suitably cured to produce a product meeting the requirements of 3.2.

3.1.1 Color: Shall be black.

3.2 Properties: The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

3.2.1 As Received:

3.2.1.1 Hardness; Durometer "A" 70 \pm 5 ASTM D2240
or equiv.

3.2.1.2 Tensile Strength, min 1000 psi ASTM D412,
(6.90 MPa) Die B or C

3.2.1.3 Elongation, min 250% ASTM D412,
Die B or C

3.2.1.4 Specific Gravity Preproduction ASTM D297
 ρ Value \pm 0.02

3.2.2 Lubricating Oil Resistance: (Immediate Deteriorated Properties)

ASTM D471
Medium: ASTM Oil No. 1
Temperature: 150°C \pm 3
(302°F \pm 5)
Time: 70 hr \pm 0.5

3.2.2.1 Hardness Change, Durometer -10 to +10
"A" or equiv.

3.2.2.2 Tensile Strength Change, -50%
max

3.2.2.3 Elongation Change, max -50%

3.2.2.4 Volume Change 0 to +10%

3.2.2.5 Decomposition None

3.2.2.6 Surface Tackiness None

3.2.3 Processing Oil Resistance: (Immediate Deteriorated Properties)

ASTM D471
Medium: ASTM Oil No. 3
Temperature: 150°C \pm 3
(302°F \pm 5)
Time: 70 hr \pm 0.5

3.2.3.1 Hardness Change, Durometer -20 to +5
"A" or equiv.

| | | | | |
|---------|---|-------------------------|--------------|--|
| 3.2.3.2 | Elongation Change, max | -70% | | |
| 3.2.3.3 | Volume Change | 0 to +45% | | |
| 3.2.3.4 | Decomposition | None | | |
| 3.2.3.5 | Surface Tackiness | None | | |
| 3.2.4 | <u>Coolant Resistance:</u> (Immediate Deteriorated Properties) | | Medium: | ASTM D471 Ethylene Glycol 97% Water 3% |
| 3.2.4.1 | Hardness Change, Durometer "A" or equiv. | -15 to +15 | Temperature: | 150°C \pm 3 (302°C \pm 5) |
| 3.2.4.2 | Tensile Strength Change, max | -25% | Time: | 70 hr \pm 0.5 |
| 3.2.4.3 | Elongation Change, max | -50% | | |
| 3.2.4.4 | Volume Change | 0 to +20% | | |
| 3.2.4.5 | Decomposition | None | | |
| 3.2.4.6 | Surface Tackiness | None | | |
| 3.2.5 | <u>Dry Heat Resistance:</u> | | | ASTM D573 |
| 3.2.5.1 | Hardness Change, Durometer "A" or equiv. | 0 to +10 | Temperature: | 100°C \pm 1 (212°F \pm 2) |
| 3.2.5.2 | Tensile Strength Change, max | -25% | Time: | 70 hr \pm 0.5 |
| 3.2.5.3 | Elongation Change, max | -40% | | |
| 3.2.5.4 | Bend (flat) | No cracking or checking | | |
| 3.2.6 | <u>Compression Set:</u> | | | ASTM D395, Method B |
| 3.2.6.1 | Percent of Original Deflection, max | 50 | Temperature: | 125°C \pm 2 (257°F \pm 4) |
| | | | Time: | 70 hr \pm 0.5 |
| 3.2.7 | <u>Low-Temperature Resistance:</u> | | | ASTM D2137, Method A |
| 3.2.7.1 | Brittleness | Pass | Temperature: | -40°C \pm 1 (-40°F \pm 2) |
| | | | Time: | 5 hr \pm 0.2 |

- 3.2.8 Weathering: The product, unless otherwise specified, shall have weather resistance acceptable to the purchaser, determined by a procedure agreed upon by purchaser and vendor.
- 3.2.9 Corrosion: The product, unless otherwise specified, shall not have a corrosive effect on other materials, when exposed to conditions normally encountered in service, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.
- 3.3 Quality: The product, as received by purchaser, shall be uniform in quality and condition, clean, smooth, as free from foreign material as commercially practicable, and free from imperfections detrimental to usage of the product.
- 3.4 Tolerances: Unless otherwise specified, the following tolerances shall apply:
- 3.4.1 Sheet and Strip:

TABLE I

| Nominal Thickness (T) Inches | Tolerance, Inch Plus and Minus | |
|---------------------------------|-----------------------------------|-----------------------|
| | Fixed | Closure (See 3.4.1.1) |
| Up to 0.400, incl | 0.008 | 0.013 |
| Over 0.400 to 0.630, incl | 0.010 | 0.016 |
| Over 0.630 to 1.000, incl | 0.013 | 0.020 |
| Over 1.000 to 1.600, incl | 0.016 | 0.025 |
| Over 1.600 to 2.500, incl | 0.020 | 0.032 |
| Over 2.500 to 4.000, incl | 0.025 | 0.040 |
| Over 4.000 to 6.300, excl | 0.032 | 0.050 |
| 6.300 and over | 0.005T | -- |

TABLE I (SI)

| Nominal Thickness (T) Millimetres | Tolerance, Millimetres Plus and Minus | |
|--------------------------------------|--|-----------------------|
| | Fixed | Closure (See 3.4.1.1) |
| Up to 10.00, incl | 0.20 | 0.32 |
| Over 10.00 to 16.00, incl | 0.25 | 0.40 |
| Over 16.00 to 25.00, incl | 0.32 | 0.50 |
| Over 25.00 to 40.00, incl | 0.40 | 0.63 |
| Over 40.00 to 63.00, incl | 0.50 | 0.80 |
| Over 63.00 to 100.00, incl | 0.63 | 1.00 |
| Over 100.00 to 160.00, excl | 0.80 | 1.25 |
| 160.00 and over | 0.005T | -- |