

**AEROSPACE
MATERIAL
SPECIFICATION****AMS 3307C**

Issued	MAY 1969
Revised	JAN 1991
Reaffirmed	NOV 2003

Superseding AMS 3307B

RUBBER, SILICONE (VMQ)
Low Compression Set, Non-Oil-Resistant
65 - 75

1. SCOPE:**1.1 Form:**

This specification covers a silicone (VMQ) rubber in the form of sheet, strip, and molded shapes.

1.2 Application:

Primarily for parts required to operate or seal from -55° to +200°C (-67° to +392°F), compounded especially for low compression set. Silicone rubber is resistant to deterioration by ozone, smog, and weathering and remains flexible over the temperature range noted. These products are not intended for use with petroleum-base fluids or lubricants. Certain design applications may cause these products to be susceptible to cutting, tearing, and abrasion.

1.3 Safety - Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2003 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER:
Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org

SAE WEB ADDRESS:
<http://www.sae.org>

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

2.1.1 Aerospace Material Specifications:

AMS 2279	Tolerances, Rubber Products
MAM 2279	Tolerances, Metric, Rubber Products
AMS 2810	Identification and Packaging, Elastomeric Products

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM D 297	Rubber Products - Chemical Analysis
ASTM D 395	Rubber Property - Compression Set
ASTM D 412	Rubber Properties in Tension
ASTM D 573	Rubber - Deterioration in an Air Oven
ASTM D 624	Rubber Property - Tear Resistance
ASTM D 1329	Evaluating Rubber Property - Retraction at Low Temperature (TR Test)
ASTM D 2240	Rubber Property - Durometer Hardness

3. TECHNICAL REQUIREMENTS:**3.1 Material:**

Shall be a compound, based on a silicone (VMQ) rubber, suitably cured to produce a product meeting the requirements of 3.2.

3.2 Properties:

The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

3.2.1 As Received:

3.2.1.1 Hardness, Durometer "A" or equivalent	70 ± 5	ASTM D 2240
3.2.1.2 Tensile Strength, minimum	800 psi (5.52 MPa)	ASTM D 412, Die B or C
3.2.1.3 Elongation, minimum	125%	ASTM D 412, Die B or C

3.2.1.4	Tear Resistance, minimum	50 pounds force per inch (8.76 kN/m)	ASTM D 624, Die B
3.2.1.5	Specific Gravity	Preproduction Value ± 0.02	ASTM D 297
3.2.2	Dry Heat Resistance:		ASTM D 573 Temperature: $225^{\circ}\text{C} \pm 3$ ($437^{\circ}\text{F} \pm 5$) Time: 22 hours ± 0.5
3.2.2.1	Hardness Change, Durometer "A" or equivalent	± 10	
3.2.2.2	Tensile Strength Change, maximum	-15%	
3.2.2.3	Elongation Change, maximum	-30%	
3.2.2.4	Bend (flat)	No cracking or checking	
3.2.3	Compression Set:		ASTM D 395, Method B Temperature: $175^{\circ}\text{C} \pm 3$ ($347^{\circ}\text{F} \pm 5$) Time: 22 hours ± 0.5
	Percent of Original Deflection, maximum	20	
3.2.4	Low-Temperature Resistance:		
3.2.4.1	Temperature Retraction, TR-10 Point, maximum	-45°C (-49°F)	ASTM D 1329, Elongate specimens 75%
3.2.5	Weathering: When specified, the product shall have weather resistance acceptable to purchaser, determined by a procedure agreed upon by purchaser and vendor.		
3.2.6	Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.		
3.3	Quality:		

The product, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign material as commercially practicable, and free from imperfections detrimental to usage of the product.

3.4 Tolerances:

φ

Shall conform to all applicable requirements of AMS 2279 or MAM 2279.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

φ

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for the following requirements are acceptance tests and shall be performed on each lot:

Requirement	Paragraph Reference
Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Specific Gravity	3.2.1.5
Compression Set	3.2.3

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of a product to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing:

φ

Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient product shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.