

AEROSPACE

MATERIAL SPECIFICATIONS

AMS 3332A

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N.Y. 10017

Issued 7-1-57
Revised 2-15-65

SILICONE RUBBER
Extreme Low Temperature Resistant
15 - 30

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. **FORM:** Sheet, strip, molded shapes, or as ordered.

3. **APPLICATION:** Primarily for rubber-like parts required to operate or seal at temperature from -75 to +230 C (-103 to +446 F), compounded especially for operation at extreme low temperatures. Silicone rubber is resistant to deterioration by weathering and by high aniline point petroleum base oils, and remains flexible over the temperature range noted. This material is not normally suitable for use in contact with low aniline point petroleum base fluids, including fuels, due to excessive swelling.

4. **TECHNICAL REQUIREMENTS:**

4.1 **General:**

4.1.1 **Condition:** Unless otherwise specified, a suitably cured product shall be furnished.

4.1.2 **Weathering:** When specified, the product shall have weather resistance acceptable to the purchaser as determined by a procedure agreed upon by purchaser and vendor.

4.1.3 **Corrosion:** The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable.

4.2 **Properties:** The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with the issue of specified ASTM methods listed in the latest issue of AMS 2350, insofar as practicable.

4.2.1 **As Received:**

4.2.1.1 Hardness, Durometer "A" or equiv.	15 - 30	ASTM D676
4.2.1.2 Tensile Strength, psi, min	400	ASTM D412, Die B or C
4.2.1.3 Elongation, %, min	350	ASTM D412, Die B or C
4.2.1.4 Tear Resistance, lb per in., min	30	ASTM D624, Die B

4.2.2 **Lubricating Oil Resistance:**

4.2.2.1 **Hardness Change, Durometer "A" or equiv.** -10 to +5

4.2.2.2 **Tensile Strength Change, %, max (based on area before immersion)** -50

4.2.2.3 **Elongation Change, %, max** -20

SAENORM.COM Click & View the full PDF of any standard

4.2.2.4	Volume Change, %	0 to +25	
4.2.2.5	Decomposition	None	
4.2.2.6	Surface Tackiness	None	
ø 4.2.3	<u>Dry Heat Resistance:</u>		ASTM D573
4.2.3.1	Hardness Change, Durometer "A" or equiv.	-5 to +10	Temperature: 225 C \pm 3 (437 F \pm 5.4) Time: 24 hr
4.2.3.2	Tensile Strength Change, %, max	-15	
4.2.3.3	Elongation Change, %, max	-20	
4.2.3.4	Bend (flat)	No cracking or checking	
ø 4.2.4	<u>Compression Set:</u>		ASTM D395, Method B
4.2.4.1	Per cent of original deflection, max	60	Temperature: 175 C \pm 3 (347 F \pm 5.4) Time: 22 hr
ø 4.2.4.2	Per cent of original thickness, max	15	
4.2.5	<u>Low Temperature Resistance:</u>		
4.2.5.1	Brittleness ø	Pass	ASTM D746, Procedure B Temperature: -80 C \pm 3 (-112 F \pm 5.4) Time: 10 min.
4.2.5.2	Young's Modulus, psi, max ø (See Note 1)	1000	ASTM D797 Temperature: -75 C \pm 3 (-103 F \pm 5.4) Time: 5 hr

Note 1. This test is not normally required but is intended to be used as a referee test in case of disagreement on the results of the brittleness test.

5. **QUALITY:** The product shall be uniform in quality and condition, clean, smooth, and free from chalky spots and foreign materials and from imperfections detrimental to fabrication, appearance, or performance of parts.

6. **TOLERANCES:** Unless otherwise specified, the following tolerances apply:

6.1 Sheet:

Nominal Thickness Inches	Tolerance, Inch Plus and Minus
Up to 1/8, incl	1/64
Over 1/8 to 1/2, incl	1/32
Over 1/2	3/64