

Type 4
25% Glass Filled Virgin Polytetrafluoroethylene (PTFE) Moldings or Extrusions

1. SCOPE:

1.1 Form:

This specification covers a polytetrafluoroethylene (PTFE) resin filled with 25% glass fiber in the form of extruded or molded rods or tubes which are sintered after molding or, in the case of extrusions, sintered during the extrusion process.

1.2 Application:

These products have been used typically for dynamic seal components requiring dimensional stability up to 450 °F (232 °C), but usage is not limited to such applications. Each application should be considered individually.

2. APPLICABLE DOCUMENTS:

See AMS 3678.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification:

The complete requirements for procuring the products described herein shall consist of this document and the latest issue of the basic specification, AMS 3678.

3.2 Material:

All products shall be molded or extruded from virgin polytetrafluoroethylene (PTFE) powder conforming to ASTM D 4894, Type II or Type IV, uniformly blended with the specified filler. The blended powder shall consist of 25% \pm 2 milled glass fibers and the remainder virgin PTFE powder, filler percentage measured by weight.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org
SAE WEB ADDRESS: <http://www.sae.org>