

**SAE** The Engineering Society  
For Advancing Mobility  
Land Sea Air and Space®  
**INTERNATIONAL**

400 Commonwealth Drive, Warrendale, PA 15096-0001

# AEROSPACE MATERIAL SPECIFICATION

**AMS 3892/2A**

Issued 11-15-72  
Revised 7-1-84

**TOW OR YARN, CARBON (GRAPHITE) FIBERS**  
For Structural Composites  
GF 300 (2070) Tensile Strength, 50 (345) Tensile Modulus

**1. SCOPE:**

1.1 **Form:** This specification covers one type of continuous multifilament carbon (graphite) fibers in the form of a tow or yarn (when twisted). The weight per unit length of the tow or yarn is governed by the filament count which is identified by the supplier's grade or material designation.

1.2 **Classification:** Carbon (graphite) tow or yarn, derived from a polyacrylonitrile precursor, with typical tensile strength over 300,000 psi (2070 MPa) and tensile modulus of 50,000,000 psi (345 GPa) for use in general purpose structural composites requiring high modulus and moderately high tensile strength.

2. **APPLICABLE DOCUMENTS:** See AMS 3892.

**3. TECHNICAL REQUIREMENTS:**

3.1 **Basic Specification:** The complete requirements for procuring the carbon (graphite) tow or yarn described herein shall consist of this document and the latest issue of the basic specification, AMS 3892.

3.2 **Storage Life:** The product shall meet the interlaminar shear strength requirements of this specification when tested at any time up to 6 months from date of receipt by purchaser provided it has been stored at room temperature in the original closed container.

3.3 **Properties:** Shall be as follows; the requirements of 3.3.1, 3.3.2, and 3.3.3 apply to the average of the number of determinations indicated in the basic specification but no individual value shall be less than 90% of the specified minimum average unless due to an obvious testing problem, in which case a substitute specimen may be tested:

3.3.1 Tensile Strength, min 300,000 psi (2070 MPa)

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

- 3.3.2 Modulus of Elasticity, min 48,500,000 psi (334,400 MPa)  
 Ø max 58,000,000 psi (400,000 MPa)
- 3.3.3 Interlaminar Shear Strength,  
 Ø min (See 8.1) 6500 psi (45 MPa)
- 3.3.4 Length per unit weight Preproduction  
 Ø Value +5%
- 3.3.5 Fiber Finish, by weight,  
 Ø max 2%
- 3.3.6 Fiber Density 0.064 - 0.067 (1.77 - 1.85 g/cm<sup>3</sup>)  
 Ø lb per cu in.
- 3.3.7 Yarn Twist (when  
 Ø (applicable), nominal 0.4 turns per in. (15 turns/m)  
 max 0.8 turns per in. (30 turns/m)
4. QUALITY ASSURANCE PROVISIONS: See 3892.
5. PREPARATION FOR DELIVERY: See AMS 3892.
6. ACKNOWLEDGMENT: See AMS 3892.
7. REJECTIONS: See AMS 3892.
8. NOTES:
- 8.1 The interlaminar shear strength values are based on the use of a high performance epoxy resin system for the laminate, such as tetraglycidyl methylene-dianiline/diamino-diphenyl sulfone or equivalent.