

# AEROSPACE MATERIAL SPECIFICATION



AMS 4307A

Issued OCT 1988  
Revised MAR 1998

Superseding AMS 4307

Submitted for recognition as an American National Standard

Aluminum Alloy, Extrusions  
6.4Zn - 2.4Mg - 2.2Cu - 0.12Zr (7150-T61511)  
Solution Heat Treated, Stress Relieved by Stretching, Straightened,  
and Precipitation Heat Treated

UNS A97150

## 1. SCOPE:

### 1.1 Form:

This specification covers an aluminum alloy in the form of extruded bars, rods, wire, profiles, and tubing.

### 1.2 Application:

These extrusions have been used typically for structural parts requiring a combination of high strength, moderate fatigue strength, and moderate exfoliation corrosion resistance (See 8.2), but usage is not limited to such applications.

## 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

- AMS 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings
- MAM 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units
- AMS 2772 Heat Treatment of Aluminum Alloy Raw Materials

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1998 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:  
TO PLACE A DOCUMENT ORDER:  
SAE WEB ADDRESS:

(724) 772-7154  
(724) 776-4970  
<http://www.sae.org>

FAX: (724) 776-0243  
FAX: (724) 776-0790

## 2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM B 594 Ultrasonic Inspection of Aluminum-Alloy Wrought Products for Aerospace Applications  
 ASTM B 645 Plane Strain Fracture Toughness Testing of Aluminum Alloys  
 ASTM B 666/B 666M Identification Marking of Aluminum and Magnesium Products

## 2.3 ANSI Publications:

Available from ANSI, 11 West 42nd Street, New York, NY 10036-8002.

ANSI H 35.2 Dimensional Tolerances for Aluminum Mill Products  
 ANSI H 35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355 or MAM 2355.

TABLE 1 - Composition

Element	min	max
Zinc	5.9	6.9
Magnesium	2.0	2.7
Copper	1.9	2.5
Zirconium	0.08	0.15
Iron	--	0.15
Silicon	--	0.12
Manganese	--	0.10
Titanium	--	0.06
Chromium	--	0.04
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

## 3.2 Condition:

Extruded, solution heat treated, stress relieved by stretching to produce a permanent set of 1.5%, but not less than 1% nor more than 3%, and precipitation heat treated to the T61511 temper (See 8.3). Heat treating furnace surveys and calibrations of temperature controllers and recorders shall be in accordance with AMS 2772 except that solution heat treating time and temperature shall be as shown for alloy 7050.

3.2.1 Extrusions may receive straightening, after stretching, of an amount necessary to meet the requirements of 3.5.

3.2.2 Extrusions shall be supplied with an as-extruded surface finish; light polishing to remove minor surface imperfections is permissible provided such imperfections can be removed within specified dimensional tolerances.

## 3.3 Properties:

Extrusions shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

3.3.1 Tensile Properties: Shall be as shown in Table 2, determined on specimens taken in the longitudinal direction.

TABLE 2A - Minimum Longitudinal Tensile Properties, Inch/Pound Units

Nominal Diameter or Least Thickness (bars, rods, wire, profiles) or Nominal Wall Thickness (tubing) Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
0.250 to 0.499, incl	87.0	82.0	8
Over 0.499 to 0.749, incl	88.0	83.0	9
Over 0.749 to 2.000, incl	89.0	84.0	8

TABLE 2B - Minimum Longitudinal Tensile Properties, SI Units

Nominal Diameter or Least Thickness (bars, rods, wire, profiles) or Nominal Wall Thickness (tubing) Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50 mm or 4D %
6.35 to 12.67, incl	600	565	8
Over 12.67 to 19.02, incl	607	572	9
Over 19.02 to 50.80, incl	614	579	8

3.3.2 Corrosion Resistance: Electrical conductivity, determined at the T/10 plane on the tensile specimens, shall be 29.0 to 32.5% IACS (International Annealed Copper Standard) (16.8 to 18.8 MS/m) (See 8.2).

#### 3.4 Quality:

Extrusions, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the extrusions.

3.4.1 When specified, extrusions shall be subjected to ultrasonic inspection in accordance with ASTM B 594.

3.4.1.1 Extrusions, 0.500 to 1.499 inches (12.70 to 38.07 mm), inclusive, in nominal thickness, not exceeding 600 pounds (272 kg) per piece, or a 10 to 1 width-to-thickness ratio shall meet ultrasonic Class B. Extrusions 1.500 inches (38.10 mm) and over in nominal thickness, not exceeding 600 pounds (272 kg) per piece, or a 10 to 1 width-to-thickness ratio, shall meet ultrasonic Class A.

#### 3.5 Tolerances:

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

### 4. QUALITY ASSURANCE PROVISIONS:

#### 4.1 Responsibility for Inspection:

The vendor of extrusions shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the extrusions conform to specified requirements.