



AEROSPACE MATERIAL SPECIFICATION

AMS4510**REV. H**

Issued 1939-12
Reaffirmed 2009-06
Revised 2015-07

Superseding AMS4510G

Phosphor Bronze, Sheet, Strip, and Plate
94.5Cu - 4.0Sn - 0.19P
Spring Temper (H08)
(Composition similar to C51000)

RATIONALE

AMS4510H revises the method of analysis for Composition (3.1), and is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a copper alloy (phosphor bronze) in the form of sheet, strip, and plate.

1.2 Application

These products have been used typically for stampings and springs, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2222 Tolerances, Copper and Copper Alloy Sheet, Strip, and Plate

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B248 General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2015 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4510H>**

ASTM B248M General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar (Metric)

ASTM E8/E8M Tension Testing of Metallic Materials

ASTM E18 Rockwell Hardness Hardness of Metallic Materials

ASTM E478 Chemical Analysis of Copper Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by ASTM E478, or by other analytical methods acceptable to purchaser.

Table 1 - Composition

Element (3.1.1)	min	max
Tin	4.2	5.8
Phosphorus	0.03	0.35
Zinc	--	0.30
Iron	--	0.10
Lead	--	0.05
Copper	--	(See 3.1.2)
Sum of Named Elements	99.5	

3.1.1 These composition limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements by agreement between the manufacturer or supplier and purchaser.

3.1.2 Copper may be reported as "remainder", or as the difference between the sum of results for all analyzed elements and 100%, or as the result of direct analysis.

3.1.3 When all named elements in Table 1 are analyzed, the sum shall be minimum, but such determination is not required for routine acceptance of each lot.

3.2 Condition

Cold rolled, spring (H08) temper (See 8.2).

3.3 Properties

The product shall conform to the following requirements.

3.3.1 Tensile Properties

Shall be 91 to 105 ksi (627 to 724 MPa), determined in accordance with ASTM E8/E8M.

3.3.2 Hardness

Shall be as shown in Table 2, or equivalent hardness (See 8.3), determined in accordance with ASTM E18.

Table 2 - Hardness

Nominal Thickness Inch	Nominal Thickness Millimeters	Hardness
Over 0.003 to 0.029, incl	Over 0.08 to 0.74	76 to 80 HR30T
Over 0.029 to 0.039, incl	Over 0.74 to 0.99	92 to 97 HRB
Over 0.039	Over 0.99	94 to 98 HRB

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances

Shall conform to AMS2222 as applicable to refractory alloys.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the specified requirements.

4.2 Classification of Tests

All technical requirements are acceptance tests and shall be performed on each lot.

4.3 Sampling and Testing

Shall be in accordance with ASTM B248 or ASTM B248M.

4.4 Reports

The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition, tensile properties, and hardness of each lot. This report shall include the purchase order number, lot number, AMS4510H, size, and quantity.

4.5 Resampling and Retesting

If any specimen used in the above tests fails to meet the specified requirements, disposition of the product may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the product represented. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY

5.1 Identification

The product shall be identified as in 5.1.1 unless line marking as in 5.1.2 is specified by purchaser.

5.1.1 Each sheet, strip, and plate shall be legibly marked near one end, coils being marked near the outside end, with AMS4510H, manufacturer's identification, and nominal thickness, using any suitable marking fluid. As an alternate method, individual pieces or bundles shall have attached a durable tag marked with the above information or shall be boxed and the box marked with the same information.

5.1.2 When specified by purchaser, each sheet, strip, and plate shall be legibly marked on one face, in the respective location indicated below, with AMS4510H, lot number, manufacturer's identification, and nominal thickness. The characters shall be applied using a suitable marking fluid removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling. The specification number, manufacturer's identification, and nominal thickness shall be continuously line marked; the lot number may be included in the line marking or may be marked at one location on each piece.