

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 4520D

Issued 1-22-40

Revised 3-1-51

BRONZE STRIP

89Cu - 4Sn - 4Pb - 3Zn

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. FORM: Strip.

3. APPLICATION: Primarily for rolled split bushings.

4. COMPOSITION:

Copper	86.7 min
Tin	3.5 - 4.5
Lead	3.5 - 4.5
Zinc	1.5 - 4.0
Iron	0.10 max
Total Named Elements	99.8 min

5. CONDITION: Cold rolled.

6. TECHNICAL REQUIREMENTS:

6.1 Tensile Properties:

Elongation, % in 2 in. 16 min

6.2 Hardness: Strip should have hardness of Rockwell B 72-79 or equivalent, but shall not be rejected on the basis of hardness if the tensile property requirement is met.

7. QUALITY: Strip shall be uniform in quality and condition, clean, sound, smooth, and free from foreign materials and from internal and external defects, detrimental to fabrication or to performance of parts.

8. TOLERANCES: Shall be as specified on the purchase order.

9. REPORTS:

9.1 Unless otherwise specified, the vendor of strip shall furnish with each shipment three copies of a report showing the results of tests to determine conformance to the requirements of this specification or stating that the chemical composition and tensile properties of the strip conform to the requirements specified. This report shall include the purchase order number, material specification number, thickness, size, and quantity.

in 7C of the SAE Technical Board rules provides that: "All technical reports, including standards, approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."