

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard



AMS 5028C

Issued
Revised

MAY 1970
OCT 1998

Superseded by AMS 5028B

(R)

Steel, Welding Wire
1.05Cr - 0.55Ni - 1.0Mo - 0.07V (0.34 - 0.40C)
Vacuum Melted, Environment-Controlled Packaging

UNS K23725

1. SCOPE:

1.1 Form:

This specification covers a low-alloy steel in the form of welding wire.

1.2 Application:

This wire has been typically used as filler metal for gas-tungsten-arc and gas-metal-arc welding of heat-treatable steels of similar composition where the weld area is required to have strength comparable to that of the parent metal after heat treating, but usage is not limited to such applications.

1.3 Classification:

Wire shall be classified as follows:

Type 1 - Bare Wire

Type 2 - Copper Coated

1.3.1 Type 1 shall be supplied unless Type 2 is specified.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1998 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

- AMS 2259 Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
 AMS 2370 Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel, Wrought Products and Forging Stock
 AMS 2814 Packaging and Marking of Packages of Welding Wire, Premium Quality
 AMS 2816 Identification, Welding Wire, Tab Marking Method
 AMS 2819 Identification, Welding Wire, Direct Color Code System
- ARP1876 Weldability Test for Weld Filler Metal Wire
 ARP4926 Alloy Verification and Chemical Composition Inspection of Welding Wire

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

- ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron
 ASTM D 2650 Chemical Composition of Gases by Mass Spectrometry

3. TECHNICAL REQUIREMENTS:

3.1 Wire Composition:

Shall conform to the percentages by weight, shown in Table 1 determined by wet chemical methods in accordance with ASTM E 350, or by spectrochemical, methods or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon (3.1.3)	0.34	0.40
Manganese	0.60	0.90
Silicon	0.15	0.30
Phosphorus	--	0.008
Sulfur	--	0.008
Chromium	0.90	1.20
Nickel	0.40	0.70
Molybdenum	0.90	1.10
Vanadium	0.05	0.10
Copper (3.1.3)	--	0.35
Hydrogen (3.1.4) (3.1.5)	--	0.0010 (10 ppm)
Oxygen (3.1.4)	--	0.0025 (25 ppm)
Nitrogen (3.1.4)	--	0.0050 (50 ppm)

- 3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259. No variation over maximum is permitted for oxygen, nitrogen, and hydrogen.
- 3.1.2 Chemical analysis of initial ingot, bar, or rod stock before drawing, other than those analyses required to be done on the finished wire, is acceptable provided the processes used for drawing or rolling, annealing, and cleaning are controlled to ensure continued conformance to composition requirements.
- 3.1.3 Shall be determined on finished wire for carbon, and on finished wire for copper if wire is supplied copper clad.
- 3.1.4 Shall be determined on finished wire, but determination is not required for cut lengths.
- 3.1.5 The hydrogen content of the wire shall be determined at final diameter in accordance with ASTM D 2650.
- 3.2 Melting Practice:
- Steel shall be multiple melted using consumable electrode practice in the remelt cycle or shall be induction melted under vacuum.
- 3.3 Condition:
- Cold drawn, bright finish, in a temper and with a surface finish which will provide proper feeding of the wire in machine welding equipment.
- 3.4 Fabrication:
- 3.4.1 Wire shall be formed from rod or bar descaled by a process which does not affect the composition of the wire.
- 3.4.2 In process annealing, if required, between cold rolling or drawing operations, shall be performed in vacuum or in protective atmosphere to avoid surface oxidation and absorption of other extraneous elements.
- 3.4.3 Butt welding is permissible provided both ends to be joined are alloy verified using a method or methods capable of distinguishing the alloy from all other alloys processed in the facility, or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding.
- 3.4.4 Drawing compounds, oxides, dirt, oil, and other foreign materials shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.
- 3.4.5 Residual elements and dissolved gases picked up during wire processing that can adversely affect the welding characteristics, the operation of the equipment or the properties of the weld metal, shall be removed.

3.4.6 When Type 2 wire is specified, the copper coating shall be clean, bright, and uniform in appearance. A maximum of four discontinuities in any 36-inch (914-mm) length are acceptable provided the exposed wire is clean and bright. The maximum allowable discontinuity size shall be 0.25 inch (6.35 mm) in length. The thickness of the copper coating shall not exceed 0.0005 inch (0.0127 mm) on the diameter.

3.5 Properties:

Wire shall conform to the following requirements:

3.5.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.

3.5.2 Spooled Wire: Shall conform to 3.5.2.1 and 3.5.2.2.

3.5.2.1 Cast: Wire, wound on standard 12-inch (305 mm) diameter spools, shall have imparted to it a curvature such that a specimen sufficient in length to form one loop with a 1-inch (25 mm) overlap, when cut from the spool and laid on a flat surface, shall form a circle 15 to 50 inches (381 to 1270 mm) in diameter.

3.5.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch (25 mm).

3.6 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.6.1 Surface irregularities inherent with a forming process which does not tear the wire surface are acceptable provided the wire conforms to the tolerances of 3.7.

3.7 Sizes and Tolerances:

Wire shall be supplied in the sizes and to the tolerances shown in 3.7.1 and 3.7.2.

3.7.1 Diameter: Shall be as shown in Table 2.

TABLE 2A - Diameter Tolerances, Inch/Pound Units

Form	Nominal Diameter Inch	Tolerance, Inch plus and minus
Cut Lengths	0.030, 0.045	0.001
Cut Lengths	0.052, 0.062, 0.078, 0.094, 0.125, 0.156, 0.188	0.002
Spools	0.007, 0.010, 0.015, 0.020	0.0005
Spools	0.030, 0.035, 0.045	0.001
Spools	0.062, 0.078, 0.094	0.002

TABLE 2B - Diameter Tolerances, SI Units

Form	Nominal Diameter Millimeters	Tolerance, Millimeter plus and minus
Cut Lengths	0.75, 1.15	0.025
Cut Lengths	1.32, 1.57, 1.98, 2.39, 3.18, 3.96, 4.78	0.05
Spools	0.18, 0.25, 0.38, 0.51	0.013
Spools	0.76, 0.89, 1.14	0.025
Spools	1.57, 1.98, 2.37	0.05

3.7.2 Length: Cut lengths shall be furnished in 18, 27, or 36-inch (457, 686, or 914-mm) lengths, as ordered, and shall not vary more than +0, -0.5 inch (-13 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1) and sizes and tolerances (3.7) and alloy verification (5.2) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Weldability (3.5.1), cast (3.5.2.1), and helix (3.5.2.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.