

# AEROSPACE MATERIAL SPECIFICATION

**SAE**

**AMS 5310G**

Issued	MAY 1944
Revised	OCT 1985
Noncurrent	NOV 1994
Cancelled	OCT 2001

Superseding	AMS 5310F
-------------	-----------

Iron Castings, Pearlitic Malleable

(Composition similar to UNS F23330)

## CANCELLATION NOTICE

This specification has been "CANCELLED" by the Aerospace Materials Division, SAE, as of October 2001. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications.

Cancelled specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of AMS 5310G

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2001 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:  
TO PLACE A DOCUMENT ORDER:  
SAE WEB ADDRESS:

(724) 772-7161  
(724) 776-4970  
<http://www.sae.org>

FAX: (724) 776-0243  
FAX: (724) 776-0790

**1. SCOPE:****1.1 Form:**

This specification covers a pearlitic malleable iron in the form of castings.

**1.2 Application:**

Primarily for general usage at both ambient and elevated temperatures where wear resistance, medium strength, or both is required.

**2. APPLICABLE DOCUMENTS:**

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

**2.1 SAE Publications:**

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

**2.1.1 Aerospace Material Specifications:**

AMS 2350	Standards and Test Methods
AMS 2635	Radiographic Inspection
AMS 2645	Fluorescent Penetrant Inspection
AMS 2694	Repair Welding of Aerospace Castings
AMS 2804	Identification, Castings

**2.2 ASTM Publications:**

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A220	Pearlitic Malleable Iron Castings
ASTM A247	Evaluating the Microstructure of Graphite in Iron Castings
ASTM A370	Mechanical Testing of Steel Products
ASTM E351	Chemical Analysis of Cast Iron - All Types
ASTM E446	Reference Radiographs for Steel Castings up to 2 in. (51 mm) in Thickness

**2.3 U.S. Government Publications:**

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

**2.3.1 Military Standards:**

MIL-STD-794      Parts and Equipment, Procedures for Packaging and Packing of

**3. TECHNICAL REQUIREMENTS:****3.1 Condition:**

Heat treated.

**3.2 Casting:**

Castings may be made by any combination of melting, casting, and heat treating processes that will develop the properties of 3.4. A melt shall be the metal poured from a single ladle of 10,000 lb (4500 kg) or less.

**3.3 Tensile Specimens:**

Not less than three tensile specimens shall be cast with each melt of metal for castings and, when requested, shall be supplied with the castings. In the case of continuous melting, at least three specimens shall be cast for each 8-hr period of casting; one specimen cast, respectively, during pouring of the first casting, approximately the middle casting, and the last casting poured during the 8-hr period. Specimens shall be of standard size as described in ASTM A220 and shall be cast to size in molds made with the regular foundry mix of sand without using chills.

**3.4 Properties:**

Castings and representative tensile specimens produced in accordance with 3.3 and heat treated with the castings they represent shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A370.

**3.4.1 Separately-Cast Specimens:****3.4.1.1 Tensile Properties: Shall be as follows:**

Tensile Strength, min	70,000 psi (485 Mpa)
Yield Strength at 0.2% Offset, min	48,000 psi (330 Mpa)
Elongation in 4D, min	5%

### 3.4.2 Castings:

3.4.2.1 Tensile Properties: Specimens cut from castings are not required for acceptance of castings; however, if tensile specimens are machined from castings, such specimens shall have the following properties:

Tensile Strength, min	52,500 psi (360 MPa)
Yield Strength at 0.2% Offset, min	36,000 psi (250 MPa)
Elongation in 4D, min	4%

3.4.2.2 Hardness: Should be 163 - 229 HB or equivalent but castings shall not be rejected on the basis of hardness if the tensile property requirements of 3.4.2.1 are met.

3.4.2.3 Microstructure: Shall consist of temper carbon particles in the form of small rounded nodules uniformly distributed in a matrix of lamellar or spheroidized pearlite, substantially free from primary graphite and massive cementite. Evaluation of microstructure with respect to type, distribution, and size shall be performed in accordance with ASTM A247.

3.4.2.4 Decarburization: When agreed upon by purchaser and vendor, decarburization of any casting surface shall be less than 0.020 in. (0.50 mm), determined as visual depletion of matrix carbide on polished specimens etched in nital etchant and examined at 100X magnification.

### 3.5 Quality:

3.5.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the castings.

3.5.1.1 Casting shall have smooth surfaces and shall be well cleaned.

3.5.2 Castings shall be produced under radiographic control. This control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

3.5.3 When specified, castings shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645.

3.5.4 Radiographic, fluorescent penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. ASTM E446 may be used to define radiographic acceptance standards.

3.5.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.

3.5.6 When permitted in writing by purchaser, defects in castings may be removed and the castings repaired by welding in accordance with AMS 2694.

#### 4. QUALITY ASSURANCE PROVISIONS:

##### 4.1 Responsibility for Inspection:

The vendor of castings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to the requirements of this specification.

##### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Except as specified in 4.2.1.1, tests to determine conformance to requirements for tensile properties of separately-cast specimens (3.4.1.1), hardness (3.4.2.2), microstructure (3.4.2.3), and quality (3.5) of the castings after heat treatment are classified as acceptance tests and shall be performed on each melt or lot as applicable.

4.2.1.1 Tensile properties of specimens cut from castings shall be determined only when specified by purchaser or when separately-cast specimens are not available. Tensile properties of separately-cast specimens need not be determined when tensile properties of specimens cut from castings are determined.

4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the first-article shipment of a casting to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

##### 4.3 Sampling:

Shall be in accordance with the following; a lot shall be all castings poured consecutively from a single melt and heat treated in a single furnace batch.

4.3.1 Three tensile specimens in accordance with 3.3 representing each lot.

4.3.2 Two preproduction castings in accordance with 4.4.1 of each part number.

4.3.3 One or more castings from each lot when properties of specimens machined from castings are required. Size, location, and number of specimens machined from castings shall be as specified on the drawing or as agreed upon by purchaser and vendor. When size, location, and number of specimens are not specified, not less than two specimens, one from the thickest section and one from the thinnest section shall be cut from a casting or castings from each lot.

#### 4.4 Approval:

- 4.4.1 Sample castings from new or reworked patterns and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.
- 4.4.2 Vendor shall establish for production of sample castings of each part number parameters for the process control factors which will produce acceptable castings; these shall constitute the approved casting procedure and shall be used for producing production castings. If necessary to make any change in parameters for the process control factors, vendor shall submit for reapproval a statement of the proposed changes in materials, processing, or both and, when requested, sample castings. Production castings incorporating the revised operations shall not be shipped prior to receipt of reapproval.
- 4.4.2.1 Control factors for producing castings include, but are not limited to, the following:
- Type of furnace
  - Furnace atmosphere
  - Fluxing or deoxidation procedure
  - Gating and risering practices
  - Metal pouring temperature; variation of  $\pm 50^{\circ}\text{F}$  ( $\pm 30^{\circ}\text{C}$ ) from the established limit is permissible
  - Solidification and cooling procedures
  - Heat treatment procedures
  - Cleaning operations
  - Methods of inspection
- 4.4.2.1.1 Any of the above process control factors for which parameters are considered proprietary by the vendor may be assigned a code designation. Each variation in such parameters shall be assigned a modified code designation.

#### 4.5 Reports:

- 4.5.1 The vendor of castings shall furnish with each shipment a report showing the results of tests on separately-cast specimens or on specimens cut from castings to determine conformance to requirements for tensile properties, hardness, and microstructure. This report shall include the purchase order number, lot number, AMS 5310G, part number, and quantity from each lot.
- 4.5.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 5310G, contractor or other direct supplier of castings, part number, and quantity. When castings for making parts are produced or purchased by the parts vendor, that vendor shall inspect castings from each lot represented to determine conformance to the requirements of this specification and shall include in the report either a statement that the castings conform or copies of laboratory reports showing the results of tests to determine conformance.