

**AEROSPACE  
MATERIAL  
SPECIFICATION**

Submitted for recognition as an American National Standard

**AMS 5605B**

Issued 11-15-71  
Revised 1-1-87

Superseding AMS 5605A

**ALLOY SHEET, STRIP, AND PLATE, CORROSION AND HEAT RESISTANT**  
41.5Ni - 16Cr - 37Fe - 2.9Cb - 1.8Ti  
Consumable Electrode or Vacuum Induction Melted  
1800°F (980°C) Solution Heat Treated

**UNS N09706**

**1. SCOPE:**

- 1.1 **Form:** This specification covers a corrosion and heat resistant nickel alloy in the form of sheet, strip, and plate 1.00 in. (25.0 mm) and under in nominal thickness.
- 1.2 **Application:** Primarily for parts requiring good machinability and high strength at room and cryogenic temperatures and for short-time use up to 1000°F (540°C), particularly for those parts which are formed or welded and then heat treated to develop required properties.

2. **APPLICABLE DOCUMENTS:** The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 **SAE Publications:** Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 **Aerospace Material Specifications:**

AMS 2262 - Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate  
MAM 2262 - Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate  
AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys  
AMS 2350 - Standards and Test Methods  
AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

**REAFFIRMED** 10/91

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials  
 ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials  
 ASTM E112 - Determining Average Grain Size  
 ASTM E290 - Semi-Guided Bend Test for Ductility of Metallic Materials  
 ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Carbon	--	0.06
Manganese	--	0.35
Silicon	--	0.35
Phosphorus	--	0.020
Sulfur	--	0.015
Chromium	14.50 - 17.50	
Nickel	39.00 - 44.00	
Columbium + Tantalum	2.50 - 3.30	
Titanium	1.50 - 2.00	
Aluminum	--	0.40
Boron	--	0.006
Copper	--	0.30
Iron	remainder	

- 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

- 3.2 Condition: The product shall be supplied in the following condition:

- 3.2.1 Sheet and Strip: Cold rolled, solution heat treated free from continuous carbide network and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to a commercial corrosion resistant steel finish as in 3.2.1.1 or 3.2.1.2, as applicable.

- 3.2.1.1 Sheet: No. 2D finish.

3.2.1.2 Strip: No. 1 Strip finish.

Ø

3.2.2 Plate: Hot rolled, solution heat treated, and descaled.

3.3 Heat Treatment: The product shall be solution heat treated to conform to the requirements of 3.4. No specific solution heat treatment is specified but it is recommended that the product be solution heat treated by heating in a suitable protective atmosphere to a temperature within the range 1750° - 1850°F (955° - 1010°C), holding at the selected temperature within +25°F (+15°C) for a time commensurate with section thickness but not less than 5 min., and cooling at a rate equivalent to air cool or faster.

3.4 Properties: The product shall conform to the following requirements:

3.4.1 As Solution Heat Treated:

3.4.1.1 Tensile Properties: Shall be as specified in Table I, determined in accordance with ASTM E8.

TABLE I

Nominal Thickness Inches	Tensile Strength psi, max	Yield Strength at 0.2% Offset psi, max	Elongation in 2 in. or 4D %, min
Up to 0.1875, incl	130,000	80,000	30
Over 0.1875	140,000	90,000	30

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa, max	Yield Strength at 0.2% Offset MPa, max	Elongation in 50 mm or 4D %, min
Up to 4.75, incl	895	550	30
Over 4.75	965	620	30

3.4.1.2 Hardness: Should be not higher than shown below or equivalent, determined in accordance with ASTM E18, but the product shall not be rejected on the basis of hardness if the tensile property requirements of 3.4.1.1 are met.

Nominal Thickness		Hardness
Inches	Millimetres	
Up to 0.1875, incl	Up to 4.75, incl	102 HRB
Over 0.1875	Over 4.75	25 HRC

- 3.4.1.3 Bending: Product 0.1875 in. (4.75 mm) and under in nominal thickness shall withstand, without cracking, bending in accordance with ASTM E290 through an angle of 180 deg around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

Nominal Thickness		Bend Factor
Inches	Millimetres	
Up to 0.050, incl	Up to 1.25, incl	1
Over 0.050 to 0.1875, incl	Over 1.25 to 4.75, incl	2

- 3.4.1.3.1 Bending requirements for product over 0.1875 in. (4.75 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

- 3.4.1.4 Grain Size: Shall be as follows, determined in accordance with ASTM E112:

Nominal Thickness		ASTM Grain Size No.
Inches	Millimetres	
Up to 0.1875, incl	Up to 4.75, incl	Predominantly 5 or finer
Over 0.1875	Over 4.75	Predominantly 4 or finer

- 3.4.2 After Precipitation Heat Treatment: The product shall have the following properties after being precipitation heat treated by heating to 1350°F + 15 (730°C + 8), holding at heat for 8 hr + 0.25, cooling at a rate of 100 F (55 C) deg per hr to 1150°F + 15 (620° + 8), holding at 1150°F + 15 (620°C + 8) for 8 hr + 0.25, and cooling in air. Instead of the 100 F (55 C) deg per hr cooling rate to 1150°F + 15 (620° + 8), the furnace cooling may be at any rate provided the time at 1150°F + 15 (620°C + 8) is adjusted to give a total precipitation heat treatment time of not less than 18 hours.

- 3.4.2.1 Tensile Properties: Shall be as specified in Table II, determined in accordance with ASTM E8.

TABLE II

Nominal Thickness Inches	Tensile Strength psi, max	Yield Strength at 0.2% Offset psi, max	Elongation in 2 in. or 4D %, min
Up to 0.1875, incl	175,000	145,000	12
Over 0.1875	170,000	140,000	12

TABLE II (SI)

Nominal Thickness Millimetres	Tensile Strength MPa, max	Yield Strength at 0.2% Offset MPa, max	Elongation in 50 mm or 4D %, min
Up to 4.75, incl	1205	1000	12
Over 4.75	1170	965	12

- 3.4.2.2 Hardness: Should be not lower than 34 HRC, or equivalent, determined in accordance with ASTM E18 but the product shall not be rejected on the basis of hardness if the tensile property requirements of 3.4.2.1 are met.

3.5 Quality:

- 3.5.1 Alloy shall be produced by multiple melting using consumable electrode practice in the remelt cycle or shall be induction melted under vacuum. If consumable electrode remelting is not performed in vacuum, electrodes which have been produced by vacuum induction melting shall be used for remelting.

- 3.5.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

- 3.6 Tolerances: Shall conform to all applicable requirements of AMS 2262 or MAM 2262.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

- 4.3 Sampling: Shall be in accordance with AMS 2371; when consumable electrode remelted alloy is supplied, a heat shall be the consumable electrode remelted ingots produced from alloy originally melted as a single furnace charge.

4.4 Reports:

- 4.4.1 The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and the results of tests on each lot to determine conformance to the other technical requirements of this specification. This report shall include the purchase order number, heat number, AMS 5605B, solution heat treatment temperature used, size, and quantity.