

AEROSPACE  
MATERIAL  
SPECIFICATION

**AMS 5717E**  
Superseding AMS 5717D

Issued 1-31-64  
Revised 1-1-82

UNS N06333

ALLOY BARS, FORGINGS, AND RINGS, CORROSION AND HEAT RESISTANT  
45.5Ni - 25.5Cr - 3.2Co - 3.2Mo - 3.2W - 18.5Fe  
Solution Heat Treated

1. SCOPE:

- 1.1 Form: This specification covers a corrosion and heat resistant nickel alloy in the form of bars, forgings, flash welded rings, and stock for forging or flash welded rings.
- 1.2 Application: Primarily for parts requiring heat and oxidation resistance up to 2150°F (1175°C), particularly where such parts may require welding during fabrication.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

# AMS 5717E

## 2.1.1 Aerospace Material Specifications:

- AMS 2241 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
- AMS 2248 - Chemical Check Analysis Limits, Wrought Heat and Corrosion and Heat Resistant Steels and Alloys, Maraging, and Other Highly-Alloyed Steels, and Iron Alloys
- AMS 2350 - Standards and Test Methods
- AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock
- AMS 2374 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Forgings and Forging Stock
- AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys
- AMS 2808 - Identification, Forgings
- AMS 7490 - Rings, Flash Welded, Corrosion and Heat Resistant Austenitic Steels and Austenitic-Type Alloys

## 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM E8 - Tension Testing of Metallic Materials
- ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
- ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

## 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

### 2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

### 2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation For Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	--	0.08
Manganese	--	2.00
Silicon	0.75 -	1.50
Phosphorus	--	0.030
Sulfur	--	0.030
Chromium	24.00 -	27.00
Nickel	44.00 -	47.00
Cobalt	2.50 -	4.00
Molybdenum	2.50 -	4.00
Tungsten	2.50 -	4.00
Copper	--	0.50
Tin	--	0.025
Lead	--	0.025
Iron	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Bars, Forgings, and Flash Welded Rings: Solution heat treated.

3.2.1.1 Bars shall be hot finished except that bars under 0.250 in. (6.25 mm) in nominal diameter or distance between parallel sides may be cold finished.

3.2.1.2 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, they shall be manufactured in accordance with AMS 7490.

3.2.2 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.

3.3 Heat Treatment: No specific heat treating instructions are specified but  $\emptyset$  bars, forgings, and flash welded rings shall be solution heat treated to produce the properties specified in 3.4.1.1 and 3.4.1.2. Recommended solution heat treatment is presented in 3.3.1.

3.3.1 Bars, forgings, and flash welded rings shall be solution heat treated by  $\emptyset$  heating to a temperature not lower than 1950°F (1065°C), holding at the selected temperature within +25°F (+15°C) for 10 min. per inch (25 mm) of cross-section, and either quenching in water or cooling rapidly in air.

# AMS 5717E

3.4 Properties: The product shall conform to the following requirements:

3.4.1 Bars, Forgings, and Flash Welded Rings:

3.4.1.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM E8:

Tensile Strength, max	120,000 psi (825 MPa)
Yield Strength at 0.2% Offset, min	35,000 psi (240 MPa)
Elongation in 4D, min	30%

3.4.1.2 Hardness: Should be not higher than 95 HRB or equivalent, determined in accordance with ASTM E18, but the product shall not be rejected on the basis of hardness if the tensile property requirements are met.

3.4.2 Stock for Forging or Flash Welded Rings: As agreed upon by purchaser and vendor.

3.5 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

3.6 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars will be acceptable in mill lengths of 6 - 24 ft (2 - 7.5 m) but not more than 25% of any shipment shall be supplied in lengths of 6 - 9 ft (2 - 3 m) except that for bars weighing over 25 lb per ft (37 kg/m), short lengths down to 2 ft (600 mm) may be supplied.

3.7 Tolerances: Unless otherwise specified, tolerances for bars shall conform to all applicable requirements of AMS 2241.

## 4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirement of this specification.

4.2 Classification of Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1 Composition (3.1) of each heat.

4.2.2 Tensile properties (3.4.1.1) and hardness (3.4.1.2) of each lot of bars, forgings, and flash welded rings.

4.2.3 Tolerances (3.7) of bars.