



400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION



AMS 5850C

Issued JUL 1961
Revised JAN 1993
Reaffirmed NOV 2000

Superseding AMS 5850B

Steel, Corrosion and Heat Resistant, Honeycomb Core Resistance Welded, Square Cell

1. SCOPE:

1.1 Form:

This specification covers a honeycomb core fabricated from a corrosion and heat resistant steel.

1.2 Application:

This product has been typically as a low-density material in brazed structures, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 5520 Steel Sheet, Strip, Foil, and Plate, Corrosion and Moderate Heat Resistant, 15Cr - 7.1Ni - 2.5Mo - 1.1Al, Solution Heat Treated, Precipitation Hardenable

2.2 U.S. Government Publications:

Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-2073-1 DOD Materiel, Procedures for Development and Application of Packaging Requirements

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:

(724) 772-7161

FAX: (724) 776-0243

TO PLACE A DOCUMENT ORDER:

(724) 776-4970

FAX: (724) 776-0790

SAE WEB ADDRESS:

<http://www.sae.org>

3. TECHNICAL REQUIREMENTS:

3.1 Material:

Shall be as specified on the drawing or purchase order.

3.2 Configuration:

Core shall have cells square in shape. Nominal configuration shall be as shown in Figure 1.

3.2.1 Node-to-Node Attachment: Node-to-node attachment between foil ribbons shall be accomplished by resistance welding.

3.2.2 Classification: Core shall be classified according to cell size, foil thickness, material, and cut edge finish (See Table 1) in accordance with the following identification system:

3.2.2.1 The identification code shall be divided into three parts: the first describes the cell size and foil thickness; the second, the foil alloy; and the third, the cut edge finish.

3.2.2.1.1 Cell size shall be shown in sixteenths of an inch (mm), foil thickness in ten-thousandths of an inch (μm). Perforation of the cell shall be shown by (P), and non-perforation by (N).

Example: Core with 3/16 inch (4.8 mm) cell size, 0.0015 inch (38 μm) thick foil, perforated, made of AMS 5520 with a core surface Finish 1 shall be identified as follows:

3-15-P, AMS 5520; Finish 1 in inch/pound units

4.8-38-P, AMS 5520; Finish 1 in SI units

3.2.3 Perforations: When perforated core is specified, each cell wall shall be perforated by means of punched or pierced holes. These holes shall be not larger than 0.030 inch (0.76 mm) in diameter. All core under 0.75 inch (19 mm) in thickness shall have not less than one hole in each cell wall; core 0.75 inch (19 mm) and over in thickness shall have not less than two holes in each cell wall per inch (25 mm) of thickness.

3.2.4 Cell Dimensions: Cell size shall be the perpendicular distance between any two of the principle cell walls located opposite and parallel to each other. An average cell size shall be determined by measuring perpendicularly across the principal walls of any 10 adjacent cells, as shown in Figure 2, and then dividing the dimension obtained by 10.

3.2.5 Cell Pitch: The cell pitch (See Figure 2) of a block of core shall conform to the dimensions given in Table 2. The longitudinal pitch shall be measured parallel to the "L" dimension; the transverse pitch, perpendicular to the "L" dimension.

3.2.6 Splices: Splices may be made by any of the approved methods shown in Figure 5 and Figure 6. Splices may be made parallel to and transverse to the longitudinal dimension of the core piece. There shall be not more than one intersection of transverse and longitudinal splices in any 12 inch (305 mm) square of core. Core containing splices shall comply with all requirements for density, dimensional accuracy, node weld strength, and other strength requirements. Where drawings require splices between core sections of dissimilar types, such splices shall be made in accordance with applicable drawings.

3.2.7 Extension of "W" Dimension: The addition of blocks of core by the method shown in Figure 4 shall not be considered a splice. Blocks joined in this manner shall be subject only to those requirements for a conventionally-made, production node weld.

3.2.8 Repairs and Inserts: When localized damage or sub-standard areas in the core material are repaired, repairs shall be made by a method shown in Figure 7. Finished core containing such repairs shall comply with all requirements for core without repairs except as noted in 3.5.2.1. The number of spliced or repaired nodes or cell walls in any area which may be covered by a 12 inch (305 mm) square shall be less than 2% of the total number of nodes or walls in the 12 inch (305 mm) square if the cells are 1/4 inch (6.4 mm) and smaller; 4% if cells are larger than 1/4 inch (6.4 mm).

3.3 Properties:

Core shall conform to the following requirements:

3.3.1 Density: The density of core blocks shall be as specified in Table 2 and shall not vary more than 8% from the nominal density specified.

3.3.2 Node Weld Strength: Shall be not less than the value given for node pull in Table 2 for the applicable core type. It shall be measured by pulling in tension a chain of 9 to 15 nodes. Not less than three rows of weld shall be used (See Figure 3). Loading shall be applied at a rate of 15 to 30 pounds force (66.7 to 133.4 N) per minute to failure.

3.4 Quality:

The core, as received by purchaser, shall be uniform in quality and free from broken cell walls, foil tears, and other imperfections detrimental to usage of the core.

3.4.1 Node Welds: Shall conform to the requirements of Table 3.

3.4.2 Cleanliness: Core shall be free from oil contaminants not readily removable by normal cleaning procedures.

3.5 Sizes and Tolerances:

3.5.1 **Sizes:** Core shall be supplied in the size ordered, with core dimensions as shown in Figure 1 where,

T = Thickness, depth, or height dimension measured parallel to the core axis.

W = Transverse dimension measured perpendicular to the "L" dimension.

L = Longitudinal or ribbon dimension measured along the direction of a ribbon.

3.5.2 Tolerances:

3.5.2.1 **Cell Sizes:** The average shall be within 6% of the nominal cell size. No single cell shall vary from the nominal cell size by more than 12% except that spliced cells may be up to 30% smaller than nominal size. Pitch, as measured over a length of 20 cells, shall not vary by more than 8% from nominal.

3.5.2.2 **Perpendicularity of Cell Walls:** The angle between the cell walls and the face surfaces shall not vary from perpendicular by more than three degrees.

3.5.2.3 **Foil Thickness:** Foil thickness shall be within 10% of the specified thickness.

3.5.2.4 **Core Thickness:** Shall be in accordance with Table 1 as applicable. The thickness shall not vary by more than 0.003 inch (0.08 mm) in any 2 inches (51 mm).

3.5.2.5 **L and W Dimensions:** Shall be not less than the nominal dimensions specified for the rough core block.

3.5.2.6 **Out of Square:** The angle between the "L" and the "W" axis of the core shall not deviate from 90 degrees by more than the values listed in Table 2. The core shall be in the relaxed condition when measurements are made.

3.5.2.7 **Foil Mismatch:** Adjacent cell wall edges shall not vary by more than the ribbon mismatch for the particular class ordered as shown in Table 1. The mismatch tolerance shall not be in addition to the thickness tolerance.

3.5.2.8 **Ribbon Burr:** The maximum layover shall not exceed the value given in Table 1.

4. QUALITY ASSURANCE PROVISIONS:**4.1 Responsibility for Inspection:**

The vendor of core shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the core conforms to the requirements of this specification.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Test for density (3.3.1), node weld strength (3.3.2), and node weld quality (3.4.1) are acceptance tests and shall be performed on each lot.
- 4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of a core to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.
 - 4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or the request for procurement.

4.3 Sampling and Testing:

Shall be as follows; a lot shall be all slices cut from a single block or belt:

- 4.3.1 For Acceptance Tests: Each block or belt or 2% of the slices from each lot.
 - 4.3.1.1 Node Weld Quality: Each node weld need not be examined, but only those in selected areas. The number and size of the selected areas shall be at the discretion of the inspector.
 - 4.3.1.2 Foil Samples: A piece of the foil used to make the block or belt of core shall be submitted to purchaser with each shipment of core. When more than one lot of foil is used to make the core in a shipment, a sample from each lot shall accompany the core. This sample shall be of the same width as the core, but not necessarily wider than 1 inch (25 mm), and 72 inches (1.8 m) long. This sample may be used to determine heat treat response, mechanical properties, and composition of the core material.
- 4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor.

4.4 Approval:

- 4.4.1 Sample core shall be approved by purchaser before core for production use is supplied, unless such approval be waived by purchaser. Results of tests on production core shall be essentially equivalent to those on the approved sample.
- 4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production core which are essentially the same as those used on the approved sample core. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and, when requested, sample core. Production core made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Reports:

The vendor of core shall furnish with each shipment a report showing the results of tests for chemical composition of each foil lot and the results of tests for density and node weld strength on each lot. This report shall include the purchase order number, lot or block number, AMS 5850C, product designation, size, quantity, foil lot number, and foil thickness of each foil lot.

4.6 Resampling and Retesting:

If any specimen used in the above tests fails to meet the specified requirements, disposition of the core may be based on the results of testing three additional specimens, cut from the same block, for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the core represented. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:**5.1 Identification:**

Each piece of core and each interior and exterior container shall be legibly identified, with not less than the following information applied to a durable tag or label, using characters which will not be obliterated by normal handling:

AMS 5850C

CORE CLASSIFICATION _____

THICKNESS, TRANSVERSE, AND LONGITUDINAL DIMENSIONS _____

COMMERCIAL ALLOY AND CONDITION OR TEMPER _____

FOIL LOT NUMBER _____

MANUFACTURER'S NAME OR TRADEMARK _____

PART NUMBER _____

CONTRACT OR PURCHASE ORDER NUMBER _____

5.2 Packaging:

- 5.2.1** Core shall be packaged and shipped in outer containers to ensure that the core, during shipment and storage, will not be permanently distorted and will be protected against damage from exposure to weather or any other normal hazard.
- 5.2.2** Containers of core shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the core to ensure carrier acceptance and safe delivery.
- 5.2.3** For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-2073-1, Commercial Level, unless Level A is specified in the request for procurement.

6. ACKNOWLEDGMENT:

A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS:

Core not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.

8. NOTES:

8.1 A change bar (|) located in the left margin is for the convenience of the user in locating areas where technical revisions, not editorial changes, have been made to the previous issue of this specification. An (R) symbol to the left of the document title indicates a complete revision of the specification, including technical revisions. Change bars and (R) are not used in original publications, nor in specifications that contain editorial changes only.

8.2 Dimensions and properties in inch/pound units are primary; dimensions and properties in SI units are shown as the approximate equivalents of the primary units and are presented only for information.

8.3 For direct U.S. Military procurement, purchase documents should specify not less than the following:

Title, number, and date of this specification

Cell size and density of core desired

Size of core slices or blocks desired

Quantity of core desired

Level A packaging, if required (See 5.2.3).

8.4 Core meeting the requirements of this specification has been classified under Federal Supply Classification (FSC) 9520.


8.5 Key Words:

Honeycomb core, steel, corrosion and heat resistant, resistance welded, square cell, low density material

PREPARED UNDER THE JURISDICTION OF AMS COMMITTEE "F"

TABLE 1 - Standard Classes of Welded Honeycomb Finishes

	Finish 1 Finished for Brazing	Finish 2 Finished for Organic Bonding	Finish 3 Semi-Finished for Machining	Finish 4 Rough Cut
Thickness Tolerance (3.5.2.4)	± 0.003 inch (± 0.08 mm)	± 0.005 inch (± 0.13 mm)	± 0.016 inch (± 0.41 mm)	$\pm 1/16$ inch (± 1.6 mm)
Ribbon Mismatch Maximum depth (3.5.2.7)	0.003 inch (0.08 mm)	0.005 inch (0.13 mm)	0.016 inch (0.41 mm)	1/16 inch (1.6 mm)
Surface Condition or Burr (3.2.6)	Maximum Layover: 0.003 inch (0.08 mm) + t	Maximum Layover: 0.005 inch (0.13 mm) + t	Maximum Layover: 0.008 inch (0.20 mm) + t	Maximum 1/6 inch (4.2 mm) deep rough cut surface condition



Note: t = foil thickness

TABLE 2A - Core Characteristics, Inch/Pound Units

Core Type	Nominal Density pounds/cubic foot (See Note 1)	Node Pull pounds/inch (L)	Longitudinal Pitch inch	Transverse Pitch inch	Out-of- Square inch per inch
1-10	16.6	45	0.105	0.073	
1-15	24.9	67			
1-20	33.2	90			
1-50	83.0	190	0.105	0.073	
2-10	8.3	45	0.2068	0.1468	
2-15	12.5	67			
2-20	16.6	90			
2-30	25.0	135			
2-40	33.2	160			
2-50	41.5	190			
2-60	50.0	210			
2-100	83.0	250	0.2068	0.1468	
3-10	5.6	45	0.295	0.240	0.042
3-15	8.3	67			0.029
3-20	11.2	90			0.021
3-25	13.8	112			0.021
3-30	16.5	135			0.014
3-40	22.0	160			
3-50	27.5	190			
3-60	33.0	210			
3-100	56.0	250	0.295	0.240	
4-10	4.3	45	0.390	0.320	0.055
4-15	6.2	67			0.039
4-20	8.3	90			0.029
4-25	10.4	112			0.029
4-30	12.5	135			0.019
4-40	16.6	160			0.014
4-50	21.0	190			
4-60	25.2	210			
4-100	42.0	250	0.390	0.320	
6-10	2.8	45	0.585	0.480	0.085
6-15	4.2	67			0.055
6-20	5.6	90			0.042
6-30	8.4	135	0.585	0.480	0.029
8-30	6.2	135	0.780	0.640	
10-30	5.0	135			
10-35	5.8	157			
10-40	6.6	160			

TABLE 2A (Continued)

Core Type	Nominal Density pounds/cubic foot (See Note 1)	Node Pull pounds/inch (L)	Longitudinal Pitch inch	Transverse Pitch inch	Out-of- Square inch per inch
12-40	5.5	160			
12-50	6.9	190			

Note 1. Figures shown apply to alloys with nominal density of 0.28 pound/cubic inch and shall be adjusted proportionately for alloys of other nominal densities.

TABLE 2B - Core Characteristics, SI Units

Core Type	Nominal Density kg/m ³ (See Note 1)	Node Pull N/m (L)	Longitudinal Pitch Millimeters	Transverse Pitch Millimeters	Out-of Square mm per mm
1.6-25	266	7,880	2.67	1.85	
1.6-38	399	11,730			
1.6-51	532	15,670			
1.6-127	1330	33,270	2.67	1.85	
3.2-25	133	7,880	5.253	3.729	
3.2-38	200	11,730			
3.2-51	266	15,760			
3.2-76	400	23,640			
3.2-102	532	28,020			
3.2-127	665	33,270			
3.2-152	801	36,780			
3.2-254	1330	43,780	5.253	3.729	
4.8-25	90	7,880	7.49	6.10	0.042
4.8-38	133	11,730			0.029
4.8-51	179	15,760			0.021
4.8-64	221	19,610			0.021
4.8-76	264	23,640			0.014
4.8-102	352	28,020			
4.8-127	441	33,270			
4.8-152	529	36,780			
4.8-254	897	43,780	7.49	6.10	
6.4-25	69	7,880	9.91	8.13	0.055
6.4-38	99	11,730			0.039
6.4-51	133	15,760			0.029
6.4-64	167	19,610			0.029
6.4-76	200	23,640			0.019
6.4-102	266	28,020			0.014
6.4-127	336	33,270			
6.4-152	404	36,780			
6.4-254	673	43,780	9.91	8.13	
9.5-25	45	7,880	14.86	12.19	0.085
9.5-38	67	11,730			0.055
9.5-51	90	15,760			0.042
9.5-76	135	23,640	14.86	12.19	0.029
12.7-76	99	23,640	19.81	16.26	
15.9-76	80	23,640			
15.9-89	93	27,500			
15.9-102	106	28,020			
19.1-102	88	28,020			
19.1-127	111	33,270			

Note 1. Figures shown apply to alloys with nominal density of 7750 kg/m³ and shall be adjusted proportionately for alloys of other nominal densities.

TABLE 3 - Node Weld Conditions

General Class of Condition	Condition	Description	Limitation
Heat-Produced Holes	Weld Porosity	Small hole up to and including 0.005 inch (0.13 mm) diameter	Max 18 per node per inch (25 mm) of "T"
	Pin Hole	Holes over 0.005 to 0.015 inch (0.13 to 0.38 mm) inclusive, in diameter	Max 4 per node per inch (25 mm) of "T"
	Small Burn-through	Holes over 0.015 to 0.30 inch (0.38 to 0.76 mm), inclusive, in diameter	Max one per node per inch (25 mm) of "T"
	Large Burn-through	Holes over 0.030 inch (0.76 mm) in diameter	Not Permissible
	All Heat-produced Holes	Overall limit, any diameter	Max 20 per node per inch (25 mm) of "T"
Heat-Produced edge burn-outs (Not applicable on Finish 3 and Finish 4).	Small Edge Notch	Burned notch at edge of node, max 0.005 inch (0.13 mm) deep, max 0.015 inch (0.38 mm) wide. Not extending into wall	Max 10% of nodes on each surface
	Large Edge Notch	Burned notch at edge of node, over 0.005 to 0.015 inch (0.13 to 0.38 mm) inclusive deep; Over 0.15 to 0.30 inch (0.38 to 0.76 mm), inclusive, wide, not extending into wall	Max 1% of nodes on each surface
	Edge Burn-out	Burned notch at edge of node, over 0.015 inch (0.38 mm) deep, or over 0.030 inch (0.76 mm) wide, or extending into wall	Not Permissible
Electrode Sticking or "pickup" defects	Blister	Raised projection, unbroken metal, narrower than node flat with or without small copper spot from electrode	Max of 2 per node per inch (25 mm) of "T"
	Pickup	Blister, unbroken, causing cell wall deformation with or without small copper spot from electrode	Max of 4 per 1000 nodes per inch (25 mm) of "T"





Figure 1



(Average cell size equals 1/10 dimension across 10 cells
= $N/10$)

Note: This core cell configuration is for clarification
of dimensions only.

FIGURE 2